




171100110142




TEST REPORT

No. NKAQ20061231

Page 1 of 3

Name of Customer	NINGBO TIANSHENG WEBBING CO.,LTD		Specification/model	---
Address	---		Trademark	---
Manufacturer	---		Characteristics	Finished
Name of sample	EAR LOOP		Level	---
Tel	13282255648		Category of safety specification	---
Art.No.	---			
Above-mentioned information by Customer-supplied				
Form of sample receipt	Delivery		Sample quantity	1
Receiving Date of Sample	2020-6-17		Test Category	Consigned test
Test Requirements	GB/T 32610-2016、FZ/T01057-2007、FZ/T01095-2002			
Test result	<p>The details of test results have been printed on the next page.</p> <div style="text-align: right;">  <p>2020-6-23 Date of issue</p> </div>			
Remarks	All the test items in this report were carried out under the environmental conditions stipulated by the corresponding standards.			

Approved by



Verified by



Typed by



Zhejiang Garment and Textile Fabric Products Quality Inspection Center

TEST REPORT

No. NKAQ20061231

Page 2 of 3

Items		Unit	Requirements	Results	Conclusions
Cleavable Arylamines (Banned Azo Dyes)	4-aminobiphenyl	mg/kg	Banned (Limits: 20)	N.D.	Pass
	benzidine	mg/kg		N.D.	
	4-chloro-o-toluidine	mg/kg		N.D.	
	2-naphthylamine	mg/kg		N.D.	
	o-aminoazotoluene	mg/kg		N.D.	
	5-nitro-o-toluidine	mg/kg		N.D.	
	p-chloroaniline	mg/kg		N.D.	
	2,4-diaminoanisole	mg/kg		N.D.	
	4,4'-diaminobiphenylmethane	mg/kg		N.D.	
	3,3'-dichlorobenzidine	mg/kg		N.D.	
	3,3'-dimethoxybenzidine	mg/kg		N.D.	
	3,3'-dimethylbenzidine	mg/kg		N.D.	
	3,3'-dimethyl-4,4'-diaminobiphenylmethane	mg/kg		N.D.	
	p-cresidine	mg/kg		N.D.	
	4,4'-Methylene-bis-(2-Chloroaniline)	mg/kg		N.D.	
	4,4'-oxydianiline	mg/kg		N.D.	
	4,4'-thiodianiline	mg/kg		N.D.	
	o-Toluidine	mg/kg		N.D.	
	2,4-toluylendiamine	mg/kg		N.D.	
	2,4,5-Trimethylaniline	mg/kg		N.D.	
o-anisidine	mg/kg	N.D.			
4-aminoazobenzene	mg/kg	N.D.			
2,4-xylidine	mg/kg	N.D.			
2,6-xylidine	mg/kg	N.D.			

N.D.= Not Detected

Detection limits: 5 mg/kg.



# Zhejiang Garment and Textile Fabric Products Quality Inspection Center

## TEST REPORT

No. NKAQ20061231

Page 3 of 3

Items	Unit	Requirements	Results	Conclusions
Fibre content	%	—	Polyester: 83.5 Spandex: 16.5	—
Formaldehyde	mg/kg	$\geq 20$	N.D. (limits: 20)	Pass
pH	—	4.0~8.5	6.3	Pass
Maximum force	N	$\geq 20$	150	Pass

This space intentionally left blank.

